

POLYMER BLENDS  
HANDBOOK

# POLYMER BLENDS HANDBOOK

Volume 1

Edited by

*L. A. Utracki*



KLUWER ACADEMIC PUBLISHERS  
DORDRECHT / BOSTON / LONDON

A C.I.P. Catalogue record for this book is available from the Library of Congress.

ISBN 1-4020-1110-5 Volume 1

ISBN 1-4020-1111-3 Volume 2

ISBN 1-4020-1114-8 Set

---

Published by Kluwer Academic Publishers,  
P.O. Box 17, 3300 AA Dordrecht, The Netherlands.

Sold and distributed in North, Central and South America  
by Kluwer Academic Publishers,  
101 Philip Drive, Norwell, MA 02061, U.S.A.

In all other countries, sold and distributed  
by Kluwer Academic Publishers,  
P.O. Box 322, 3300 AH Dordrecht, The Netherlands.

*Printed on acid-free paper*

All Rights Reserved

© 2002 Kluwer Academic Publishers

No part of this work may be reproduced, stored in a retrieval system, or transmitted in any form or by any means, electronic, mechanical, photocopying, microfilming, recording or otherwise, without written permission from the Publisher, with the exception of any material supplied specifically for the purpose of being entered and executed on a computer system, for exclusive use by the purchaser of the work.

Printed in the Netherlands.

## LIST OF AUTHORS

*Dr. ABDELLAH AJJI*

**National Research Council Canada,**  
Industrial Materials Institute,  
75 de Mortagne, Boucherville,  
QC, Canada J4B 6Y4,  
Tel: +1 (450) 641-5244; Fax: +1 (450) 641-5105  
E-mail: <[abdellah.ajji@nrc.ca](mailto:abdellah.ajji@nrc.ca)>

*Dr. MICHEL M. DUMOULIN*

**National Research Council Canada,**  
Industrial Materials Institute,  
75 de Mortagne, Boucherville,  
QC, Canada J4B 6Y4,  
Tel: +1 (450) 641-5181; Fax: +1 (450) 641-5105  
E-mail: <[michel.dumoulin@nrc.ca](mailto:michel.dumoulin@nrc.ca)>

*Dr. KRIS AKKAPEDDI*

**Honeywell International,**  
Nylon Systems, Specialty Materials Division  
101 Columbia Rd.  
Morristown, NJ 07962, USA  
Tel: +1 (973) 455-3231; Fax: +1 (973) 455-4892  
E-mail: <[Kris.Akkapeddi@honeywell.com](mailto:Kris.Akkapeddi@honeywell.com)>

*Dr Eng. VALIJA EVERAERT*

**Centexbel**  
Technologiepark 7  
B-9052 Zwijnaarde, Belgium  
Tel: +32 (9) 2438235; Fax: +32 (9) 2204955  
E-mail: <[valja.everaert@centexbel.ac.be](mailto:valja.everaert@centexbel.ac.be)>

*Dr. KAMARUDIN BAHARI*

**Malaysian Institute for Nuclear Technology  
Research,**  
Radiation Processing Technology Division,  
Bangi, 43000 Kajang, Malaysia  
Tel: +60 (3) 8925-0510; Fax: +60 (3) 8920-2968  
E-mail: <[kbahari@mint.gov.my](mailto:kbahari@mint.gov.my)>

*Professor LLOYD A. GOETTLER*

**The University of Akron**  
Department of Polymer Engineering  
Akron, OH 44325-0301, USA,  
Tel: +1 (330) 972-7467, Fax: +1 (330) 258-2339  
E-mail: <[lagoett@uakron.edu](mailto:lagoett@uakron.edu)>

*Dr. S. BRUCE BROWN*

**General Electric Co.**  
R&D Center, K-1/3A71,  
One Research Circle,  
Niskayuna, NY 12309, USA,  
Tel: (518) 387-6607; Fax: (518) 387-7751,  
E-mail: <[brownsb@crd.ge.com](mailto:brownsb@crd.ge.com)>

*Professor SUAT HONG, GOH*

**National University of Singapore,**  
Department of Chemistry,  
3 Science Drive 3  
Singapore 117543  
Tel: +(65)-874-2844; Fax: +(65)-779-1691  
E-mail: <[chmgohsh@leonis.nus.edu.sg](mailto:chmgohsh@leonis.nus.edu.sg)>

*Professor JOHN M. G. COWIE*

**Heriot-Watt University,**  
Department of Chemistry,  
Edinburgh, SCOTLAND EH14 4AS,  
Tel: +44 (0131) 451-3106; Fax: +44 (0131) 451-3180  
E-mail: <[j.m.g.cowie@hw.ac.uk](mailto:j.m.g.cowie@hw.ac.uk)>

*Professor GABRIËL GROENINCKX*

**Catholic University of Leuven,**  
Department of Chemistry,  
Laboratory of Macromolecular Structural Chemistry,  
Celestijnenlaan 200F, 3001 Heverlee, Belgium,  
Tel: +32 (16) 327-440; Fax: +32 (16) 327-990  
E-mail: <[gabriel.groeninckx@chem.kuleuven.ac.be](mailto:gabriel.groeninckx@chem.kuleuven.ac.be)>

*Dr. MARIA RONG HU*  
**Atofina Chemicals, Inc.**  
900 First Ave.  
King of Prussia, PA 19406, USA  
Tel: +1 (610) 878-6703; Fax: +1 (610) 878-6260  
E-mail: <[maria.hu@atofina.com](mailto:maria.hu@atofina.com)>

*Professor TAKASHI INOUE*  
**Yamagata University,**  
Department of Polymer Science and Engineering,  
992-8510 Yonezawa, Japan,  
Tel: +81 (0238) 26-3060; Fax: +81 (0238) 26-3060  
E-mail: <[tinoue@yz.yamagata-u.ac.jp](mailto:tinoue@yz.yamagata-u.ac.jp)>

*Professor MUSA R KAMAL*  
**McGill University,**  
Department of Chemical Engineering,  
3480 University Street,  
Montreal, QC, Canada H3A 2A7,  
Tel: +1 (514) 398 4262; Fax: +1 (514) 398 6678  
E-mail: <[kamal@chemeng.lan.mcgill.ca](mailto:kamal@chemeng.lan.mcgill.ca)>

*Dr. I. J. McEWEN*  
Department of Chemistry,  
**Heriot-Watt University,**  
Edinburgh EH14 4AS, Scotland

*Dr. R. McINTYRE*  
**Millenium Inorganic Chemicals**  
PO Box 26  
Grimsby, NE Lincolnshire DN37 8DP, UK

*Professor SONJA KRAUSE*  
**Rensselaer Polytechnic Institute,**  
Department of Chemistry,  
Troy, NY 12180, USA,  
Tel: +1 (518) 276- 8445; Fax: +1 (518) 276-4887  
E-mail: <[krauss@rpi.edu](mailto:krauss@rpi.edu)>

*Dr. V. N. S. PENDYALA*  
**Indian Petrochemicals Corporation Ltd.,**  
Research Centre,  
Distr. Vadodara 391 346, Gujarat, India,  
Tel: +91 (265) 272011/272031;  
Fax: +91 (265) 272098 /270040  
E-mail: <[pendyala\\_ipcl@yahoo.co.in](mailto:pendyala_ipcl@yahoo.co.in)>

*Dr. LLOYD M. ROBESON*  
**Air Products and Chemicals, Inc.,**  
Corporate Science and Technology Center,  
7201 Hamilton Blvd, Allentown, PA 18195, USA,  
Tel: +1 (610) 481-5026; Fax: +1 (610) 481-6517  
E-mail: <[robosolm@apci.com](mailto:robosolm@apci.com)>

*Dr. JAMES J. SCOBBO, Jr.*  
**General Electric Plastics,**  
Structured Products  
Bldg. 4, 1 Lexan Lane,  
Mt. Vernon IN, 47620, U.S.A  
Tel: +1 (812) 831-7103, dial comm: 8\*393-7103  
Fax: +1 (812) 831-4955, dial comm: 8\*393-4955  
E-mail: <[jim.scobbo@gep.ge.com](mailto:jim.scobbo@gep.ge.com)>

*Dr. GERARD Z.-H. SHI*  
**Rehau Inc.,**  
P.O. Box 1706,  
1501 Edwards Ferry Road,  
Leesburg, VA-20176, USA,  
Tel: +1 (703) 777-5255, ext. 2129;  
Fax: +1 (703) 777-3053  
E-mail: <[gerard.shi@rehau-na.com](mailto:gerard.shi@rehau-na.com)>

*Dr. AJIT SINGH*  
822 Gulfview Place, Victoria,  
BC V8Y 2R6, Canada,  
Tel: +1 (250) 658-5575  
E-mail: <[singhaha@islandnet.com](mailto:singhaha@islandnet.com)>

*Professor LESLIE H. SPERLING*

**Lehigh University,**

Materials Research Center, Whitaker Lab.,

5 E. Packer Ave.,

Bethlehem, PA 18015-3194, USA,

Tel: +1 (610) 758-3845; Fax: +1 (610) 758-3526

E-mail: <[lhs0@lehigh.edu](mailto:lhs0@lehigh.edu)>

*Dr. LESZEK A. UTRACKI*

**National Research Council Canada,**

Industrial Materials Institute,

75 de Mortagne,

Boucherville, QC, Canada J4B 6Y4,

Tel: +1 (450) 641-5182; Fax: +1 (450) 641-5105

E-mail: <[leszek.utracki@nrc.ca](mailto:leszek.utracki@nrc.ca)>

*Dr. MYRIAM VANNESTE*

**Centexbel**

Technologiepark 7

B-9052 Zwijnaarde, Belgium

Tel.: +32 (9) 2438235; Fax: +32 (9) 2204955

E-mail: <[myriam.vanneste@centexbel.ac.be](mailto:myriam.vanneste@centexbel.ac.be)>

*Dr. S. FRANCIS XAVIER*

**Indian Petrochemicals Corporation Ltd.,**

Distr. Vadodara, 391 346 Gujarat, India,

Tel: +91 (265) 272011/272031 Ext. 3113;

Fax: +91 (265) 272098 / 270040

E-mail: <[francis1951@yahoo.com](mailto:francis1951@yahoo.com)>

## PREFACE

Science as a methodical investigation of Nature's capacities evolved from the humble craft tradition. Its goal is to provide the most general and the simplest possible description of the observable character of Nature. In the past the singular concept of "science" comprised all aspects of intellectual endeavor: the arts, the sciences and the crafts. It was Diderot's *Encyclopédie ou Dictionnaire Raisonné des Sciences, des Arts et des Métiers* of 1751-66 that first divided the old "science" into these three parts. The next split — that between the basic and applied sciences — is barely a century old. Basic science has been described as motivated by the desire to discover connections between natural phenomena, while applied science is the application of the discovered laws of nature for the material benefits of mankind. The boundary between the two is not rigid since experimental observation frequently provides a spur to fundamental discoveries.

In the golden times of the scientific institutions in Europe and North America, the most prominent scientists, often the Nobel Prize winners directed the work. In the USA, during the years 1945-75, basic scientific research was considered "essential for the national security, economic growth and survival of the basic democratic values" [J. Krige & D. Pestre, *Science in the 20th Century*, 1997]. In the 1960s several major corporations supported research institutes with total freedom of the research topics.

During last two decades of the twentieth century there has been an apparent reversal in the appreciation of science. Except for a few domains (*e.g.*, astrophysics or atomic physics, project *genome*), intellectual efforts are being directed toward short-term developmental work of a commercially pertinent nature. This tendency is global, evident in the industrial, academic as well as state-supported laboratories. The CEOs hired for a contract to manage an institution are focused on the present. Managing has become a profession divorced from technical knowledge — a research institute, finance company, or pig farm may "benefit" from guidance by the same person. These tendencies are reflected in the evolution of polymer science and technology.

The history of synthetic polymers is incredibly short. The term, *polymer*, was introduced in 1832. The first synthetic polymer (phenol-formaldehyde) was commercialized as *Bakelite*<sup>TM</sup> in 1909, while the first thermoplastic (polystyrene, *Trolitul*<sup>TM</sup>) six years later. The early polymer industry was developed by entrepreneurs that had little if any technical background. The commercial successes (and less known, but more numerous failures) predated even the fundamental idea of what constitutes the polymeric species. As late as 1926, Hermann Staudinger unsuccessfully advocated the concept of a linear, covalently bonded macromolecule. This idea was finally accepted during the *Faraday Society* meeting in 1935, only after Carothers reported on his polymerization studies, and demonstrated the validity of the polycondensation theory, developed by his younger colleague from du Pont de Nemours, Paul Flory. The theory provided the relationships between the molecular weights and the reaction kinetics, thus making it possible to ascertain validity of the newly formulated polycondensation principles that postulated sequential addition of bi-functional units to form linear macromolecules.

In 1900 the world production of plastics was 25 kton, doubling during the following 30 years, then re-doubling in five. The most spectacular growth was recorded in the early 1940s when the demand created by the convulsions of World War II engendered a spectacular growth of 25% per annum. During the first 30 post-war years the global plastics' industry sustained an average growth rate of 15%/year. By 1992 the world production of plastics had reached 102 million m<sup>3</sup>/year, while that of steel was 50 million m<sup>3</sup>/year. Furthermore, from 1980 to 1990 plastics production increased by 62% while that of steel decreased by 21%. Only during the past 20 years or so has plastics consumption shown smaller and more erratic advances. It is expected that by the year 2000 the world production of plastics will be 151 million tons/year. Considering the uneven polymer consumption around the world, polymer production has the potential to increase tenfold by the mid-21st century. Polymers are the fastest growing structural materials.

Rubber blending predates that of thermoplastics by nearly a century. In 1846 Parkes introduced the first blends of trans- and cis-1,4-polyisoprene, i.e., natural rubber (NR) with gutta-percha (GP). By varying the composition and/or adding fillers the blends were formed into a variety of flexible or rigid articles.

Polymer blends were developed alongside the emerging polymers. Once nitrocellulose (NC) was invented, it was mixed with NR. Blends of NC with NR were patented in 1865 — three years before the commercialization of NC. The first compatibilization of polyvinylchloride (PVC) by blending with polyvinylacetate (PVAc) and their copolymers date from 1928. PVC was commercialized in 1931 while its blends with nitrile rubber (NBR) were patented in 1936 — two years after the NBR patent was issued. The modern era of polymer blending began in 1960, after Alan Hay discovered the oxidative polymerization of 2,4-xylenols that led to polyphenyleneether (PPE). Its blends with styrenics, *Noryl*<sup>TM</sup>, were commercialized in 1965.

At present, polymer alloys, blends, and composites consume over 80 wt% of all plastics.

In addition, the polymer blends segment of the plastics' industry increases at about three times faster than the whole plastics' industry. Blending has been recognized as the most versatile, economic method to produce materials able to satisfy complex demands for performance. By the year 2000 the world market for polymer blends is expected to reach 51 million tons per annum, worth well over US\$ 200 billion. The tendency is to offer blends that can be treated as any other resin on the market; hence their processability must closely match that of single-phase polymer, but offer a much greater range of performance possibilities.

In the economically advanced countries, plastics have displaced conventional materials for most applications. Today the market pressure forces the resin manufacturers to provide better, more economic materials with superior combinations of properties, not as a replacement for wood or steel, but rather to replace the more traditional polymers. This has resulted in:

- Increased scale of production.
- Use of multicomponent and multiphase materials.
- New processing methods.

For example, twin-screw extruders with 80 tons/hr throughput and injection (100,000 kN) molding presses with shot size of 100 liters of polymer are available. Composites where the matrix is a polymer blend that comprises six different polymers have been introduced. Gas and multiple injection processes, melt-core technology, solid-state forming, microcellular foams all lead to new products with advanced performance. The polymer industry is becoming increasingly sophisticated.

To support these new tendencies the research community has been asked to provide better predictive methods for the multicomponent blends as well as improved sensors for the closed-loop process control. In particular, the evolution of morphology during the compounding and processing steps is of paramount importance. Microrheology and coalescence are the keys to describing the structure evolution of polymer blends.



In the early 1990s, the first mathematical models capable of predicting the evolution of morphology during compounding of polymer blends were developed. The fully predictive model provided good agreement with the experimentally determined variation of morphology inside a twin-screw extruder. However, it must be recognized that the morphology developed inside the compounding or the processing unit is dynamic. Upon removal of stress and in the absence of effective compatibilization the morphology changes with time.

Today, very few unmodified resins are being used. Some polymers require less modification than others. For example, the semi-crystalline polymers that already have a two-phase structure may need modification less urgently. By contrast, the amorphous resins, such as PVC, PS, PPE, or polycarbonate of bis-phenol-A (PC), are brittle and require blending more frequently. The advantages of blending fall into two categories.

**A.** Blending may improve resin or product performance by:

1. Producing materials having a full set of the desired properties at lowest cost.
  2. Extending the engineering resins' performance by incorporation of less expensive polymers.
  3. Improvement of specific properties.
    - Toughening brittle polymers, thus eliminating the need to use low molecular weight additives (*e.g.*, plasticizer in the flexible PVC formulations).
    - Blending with more rigid and more heat resistant resin may lead to improved modulus and dimensional stability.
    - Incorporation of semicrystalline polymer into an amorphous resin to improve solvent and chemical resistance (*e.g.*, in blends of PC with PEST).
    - Incorporation of non-flammable resin into a flammable one improves flame resistance (*e.g.*, styrenics or acrylics with PVC).
    - Blends with polymers having either –OH or –SH functionality leads to permanently anti-static blends (*e.g.*, ethylene oxide-co-epichlorohydrin with ABS/PC blend).
    - Biodegradable materials produced by incorporation of a biodegradable resin.
- Blending makes it possible to produce integrated multi-layer structures.
4. Providing means for recycling of industrial and/or municipal plastics waste.
  5. The blending technology makes it possible to rebuild high molecular weights of partially degraded polymers, thus to produce high performance articles from the plastics waste.
- B.** Blending may lead to improved processability:
1. Incorporation of a miscible resin with a lower glass transition temperature ( $T_g$ ) makes it possible to process the high  $T_g$  resin at temperatures well below the thermal degradation limit (*e.g.*, PS/PPE blends).
  2. Incorporation of an immiscible, low viscosity resin makes it possible to reduce pressure drop across dies or runners, thereby increasing productivity (*e.g.*, LCP/PEEK blends).
  3. Blending with resin that either by itself shows high strain hardening (SH) (*e.g.*, LDPE in blends with another PO), or when reactively blended forms long chain branches (*e.g.*, PS in blends with PO) results in blends having a controllable degree of SH. These materials show better processability in technologies where the extensional flow field is important, viz., film blowing, blow molding, wire coating, foaming, etc.
  4. Incorporation of elastomeric particles improves nucleation of gas bubbles, hence it stabilizes the foaming process, reduces bubble size and the final foam density.
  5. Incorporation of a degradable resin into an engineering or specialty one provides the means for generation of a controllable amount of the foaming gas during the ensuing stages of processing, viz., injection molding.
  6. Blending different grades of the same resin broadens the molecular weight distribution, which in turn results in easier, more stable processing (as well as better mechanical performance).
  7. Blending improves product uniformity (scrap reduction) and plant economy.
  8. Blending ascertains quick formulation changes, thus plant flexibility and productivity.

9. Blending reduces the number of grades that need to be manufactured and stored.
10. Blending technology offers methods for producing higher esthetic value materials, e.g., films or coatings without gel particles (or “fish eyes”), moldings with streak-free surface finish, etc.

The aim of the *Polymer Blends Handbook (PBH)* is to provide the most comprehensive information on all aspects of polymer blend science and technology. The book will be useful for students entering the field as well as to seasoned professionals. The contributors to *PBH* are renowned experts from eight countries and four continents, who work in academe, government laboratories and industry.

In consequence, the book may be considered comprising two parts: 1. Fundamental principles (nine chapters), and 2. Technology (eight chapters and four Appendices). Each chapter provides an introduction to the pertinent topic, discusses the principal aspects, the typical approaches used by the experts in the area, provides numerical values of pertinent parameters, and gives extensive references that facilitate further topical studies.

PBH comprises seventeen chapters that contain 1. *Introduction to polymer blends*, 2. *Thermodynamics*, 3. *Crystallization*, 4. *Interphase and compatibilization by addition of a compatibilizer*, 5. *Reactive compatibilization*, 6. *Interpenetrating Polymer Networks*, 7. *Rheology*, 8. *Morphology*, 9. *Compounding*, 10. *Processing*, 11. *Use of radiation*, 12. *Properties and performance*, 13. *Applications*, 14. *Degradation and aging*, 15. *Commercial blends*, 16. *Role of polymer blends' technology in polymer recycling*, and 17. *Perspectives*. Furthermore, the Appendices provide information on 1. *International abbreviations for polymers and polymer processing*, 2. *Miscible polymer blends*, 3. *Examples of commercial polymer blends*, and 4. *Dictionary of terms used in polymer science & technology*.

Finally, the Editor wishes to express thanks and personal appreciation to the contributors. They invested much time outside their regular duties, collecting the material and setting it into uniform text. They showed a high spirit of cooperation and great patience. The *Polymer Blends Handbook* is a testimonial of their efforts.

L. A. Utracki, Editor

Montreal, 25.12.1999

## CONTENTS

<b>List of Authors</b> .....	v
<b>Preface</b> .....	ix
<b>1. Introduction to Polymer Blends</b> .....	1
<i>L. A. Utracki</i>	
1.1 Early polymer industry .....	2
1.2 Polymer structure and nomenclature .....	7
1.3 Introduction to polymer blends .....	12
1.4 Commodity resins and their blends .....	24
1.5 Engineering resins and their blends .....	64
1.6 Specialty polymers and their blends .....	80
1.7 Biodegradable blends .....	93
1.8 Blending and recycling .....	93
1.9 Conclusions and outlook .....	95
1.10 References .....	96
<b>2. Thermodynamics of Polymer Blends</b> .....	123
<i>L. A. Utracki</i>	
2.1 Introduction .....	123
2.2 Thermodynamic principles .....	124
2.3 Thermodynamics of a single component systems .....	127
2.4 Polymeric liquid mixtures .....	134
2.5 Theories of liquid mixtures .....	138
2.6 Phase separation .....	168
2.7 Methods of measurements .....	175
2.8 Summary and conclusions .....	193
2.9 List of abbreviations .....	194
2.10 References .....	194
<b>3. Crystallization, Morphological Structure, and Melting of Polymer Blends</b> .....	203
<i>G. Groeninckx, M. Vanneste and V. Everaert</i>	
3.1 Abstract .....	203
3.2 General introduction .....	204
3.3 Crystallization, morphological structure, and melting behavior of miscible polymer blends .....	205
3.4 Crystallization, morphological structure and melting behavior of immiscible polymer blends .....	241
3.5 Nomenclature .....	285
3.6 References .....	289

<b>4.</b>	<b>Interphase and Compatibilization by Addition of a Compatibilizer</b> .....	295
	<i>A. Ajji</i>	
4.1	Introduction .....	295
4.2	Theoretical aspects of the interface .....	296
4.3	Determination of the interfacial parameters .....	308
4.4	Compatibilization by addition of a compatibilizer .....	316
4.5	Patented blends with added compatibilizer .....	326
4.6	Conclusions and outlook .....	329
4.7	References. ....	331
4.8	Nomenclature .....	336
<b>5</b>	<b>Reactive Compatibilization of Polymer Blends</b> .....	339
	<i>S. B. Brown</i>	
5.1	Introduction and purpose .....	339
5.2	Definitions of compatibilization and polymer alloys .....	341
5.3	Types of polymer blends .....	342
5.4	Characteristics of immiscible polymer blends .....	343
5.5	General strategies for compatibilization of immiscible polymer blends .....	345
5.6	Compatibilization by redistribution to produce block and random copolymer .....	347
5.7	Compatibilization by graft copolymer formation .....	352
5.8	Compatibilization by block copolymer formation .....	381
5.9	Compatibilization by direct covalent crosslinking .....	388
5.10	Compatibilization by covalent crosslinking mediated by an activating agent .....	394
5.11	Compatibilization by covalent crosslinking mediated by a coupling agent .....	398
5.12	Compatibilization by ionic interaction .....	401
5.13	Summary .....	404
5.14	References .....	405
5.15	Abbreviations .....	414
<b>6.</b>	<b>Interpenetrating Polymer Networks</b> .....	417
	<i>L. H. Sperling and R. Hu</i>	
6.1	Introduction .....	417
6.2	Synthetic methods .....	419
6.3	Morphology and glass transitions .....	421
6.4	Latex-based materials .....	427
6.5	Actual and proposed applications of IPNs .....	438
6.6	Summary .....	442
6.7	Abbreviations and acronyms .....	442
6.8	References .....	443
<b>7.</b>	<b>The Rheology of Polymer Alloys and Blends</b> .....	449
	<i>L. A. Utracki and M. R. Kamal</i>	
7.1	Introduction .....	449
7.2	Rheological models for miscible blends .....	457

7.3	Model systems for immiscible blends	458
7.4	Rheology of miscible blends	482
7.5	Rheology of immiscible blends	489
7.6	Conclusions	523
7.7	References	524
7.8	Notation and abbreviations	535
7.9	Appendices	537
<b>8.</b>	<b>Morphology of Polymer Blends</b>	<b>547</b>
	<i>Takashi Inoue</i>	
8.1	Abstract	547
8.2	Introduction	548
8.3	Microscopic methods	548
8.4	Quantification of morphology	556
8.5	Crystallization from a single-phase mixture	558
8.6	Spinodal decomposition under non-iso-quench depth	562
8.7	Melt blending of highly immiscible polymers	567
8.8	"Structure" in single phase mixtures	571
8.9	Concluding remarks	572
8.10	Acknowledgement	572
8.11	Nomenclature	572
8.12	References	574
<b>9.</b>	<b>Compounding Polymer Blends</b>	<b>577</b>
	<i>L. A. Utracki and G. Z.-H. Shi</i>	
9.1	Fundamentals of polymer mixing	577
9.2	Blending methods and equipment	601
9.3	Non-mechanical methods of polymer blending	625
9.4	Reactive processing (compatibilization)	631
9.5	Summary	640
9.6	References	641
9.7	Nomenclature and abbreviations	650
<b>10.</b>	<b>Polymer Blends Forming</b>	<b>653</b>
	<i>Michel M. Dumoulin</i>	
10.1	Abstract	653
10.2	Introduction to polymer forming	654
10.3	Forming polymer blends	660
10.4	Extrusion	686
10.5	Injection molding	699
10.6	Blow molding	727
10.7	Other forming processes	732
10.8	Forming of filled and/or reinforced blends	742
10.9	Quality and process control	745

10.10	Reprocessing	748
10.11	Conclusions	750
10.12	References	752
10.13	Notation and abbreviations	754
<b>11.</b>	<b>Use of high-energy radiation in polymer blends technology</b>	<b>757</b>
	<i>A. Singh and K. Bahari</i>	
11.1	Introduction	758
11.2	Radiation chemistry of organic compounds	758
11.3	Radiation effects on polymers	764
11.4	Irradiation of polymer blends	774
11.5	Concluding remarks	853
11.6	Acknowledgement	854
11.7	References	854
<b>12.</b>	<b>Properties and Performance of Polymer Blends</b>	<b>861</b>
	<i>S. F. Xavier</i>	
12.1	Abstract	861
12.2	Introduction	862
12.3	Low speed mechanical properties	863
12.4	High-speed mechanical properties	872
12.5	Miscibility and solubility (by <i>V. N. S. Pendyala</i> )	894
12.6	Thermal properties	905
12.7	Flammability	915
12.8	Other properties	922
12.9	Conclusions	930
12.10	Acknowledgement	931
12.11	References	931
12.12	Appendices	942
<b>13.</b>	<b>Applications of Polymer Alloys and Blends</b>	<b>951</b>
	<i>J. J. Scobbo, Jr. and L. A. Goettler</i>	
13.1	General Principles for the Use of Polymer Blends	951
13.2	Automotive applications	954
13.3	Lawn and garden	964
13.4	Electrical and Electronics Applications	965
13.5	Medical Applications	967
13.6	Building and Construction	969
13.7	Business Machines and Communications	970
13.8	Packaging	973
13.9	Miscellaneous	974
13.10	References	975
13.11	List of abbreviations	976

<b>14</b>	<b>Aging and Degradation of Polymer Blends</b> .....	977
	<i>J. M. G. Cowie I. J. McEwen and R. McIntyre</i>	
14.1	Abstract .....	977
14.2	Introduction .....	978
14.3	Physical aging .....	978
14.4	Chemical aging .....	1000
14.5	Weathering of polymer blends .....	1005
14.6	Summary, conclusions and outlook .....	1014
14.7	References .....	1015
<b>15</b>	<b>Commercial Polymer Blends</b> .....	1023
	<i>M. K. Akkapeddi</i>	
15.1	Abstract .....	1023
15.2	Introduction .....	1024
15.3	Polyolefin blends .....	1032
15.4	Styrenic blends .....	1042
15.5	Vinyl resin blends .....	1053
15.6	Acrylic blends .....	1056
15.7	Elastomeric blends .....	1058
15.8	Polyamide blends .....	1063
15.9	Polycarbonate blends .....	1082
15.10	Polyoxymethylene blends .....	1092
15.11	Polyphenyleneether (PPE) blends .....	1093
15.12	Thermoplastic polyester blends .....	1097
15.13	Specialty polymer blends .....	1101
15.14	Thermoset blend systems .....	1106
15.15	Conclusions .....	1110
15.16	References .....	1110
<b>16.</b>	<b>Role of Polymer Blends' Technology in Polymer Recycling</b> .....	1117
	<i>L. A. Utracki</i>	
16.1	Abstract .....	1117
16.2	Introduction .....	1117
16.3	The principles of polymer blending .....	1126
16.4	Principles of polymer degradation and stabilization .....	1131
16.5	Use of polymer blend technology in plastics recycling .....	1137
16.6	Polymer blends' recycling .....	1139
16.7	Post-consumer waste (PCW) recycling .....	1146
16.8	Biodegradable blends .....	1151
16.9	Conclusions .....	1157
16.10	Nomenclature .....	1158
16.11	References .....	1160

<b>17. Perspectives in Polymer Blend Technology</b> .....	1167
<i>L. M. Robeson</i>	
17.1 The past and present: relevance to the future .....	1167
17.2 Perspectives in the future developments in commodity polymer blends .....	1171
17.3 Engineering polymer blends: future perspective .....	1174
17.4 High temperature polymer blends .....	1178
17.5 Electrically conductive polymer blends .....	1182
17.6 Biodegradable polymer blends .....	1186
17.7 Future trends in the science and technology of polymer blends .....	1187
17.8 Additional areas of emerging and future blend technology .....	1190
17.9 Postscript .....	1194
17.10 References .....	1194
<b>APPENDIX I. International Abbreviations For Polymers And Polymer Processing</b> .....	1201
<i>compiled by L. A. Utracki</i>	
<b>APPENDIX II. Miscible Polymer Blends</b> .....	1215
<i>prepared by S. Krause and S. H. Goh</i>	
1. Introductory remarks .....	
2. Table I Chemically dissimilar polymer pairs miscible in the amorphous state at room temperature. ....	1219
3. Table II Polymer pairs containing one monomer in common, miscible in the amorphous state at room temperature. ....	1269
4. Table III Chemically dissimilar polymer triads (and tetrads) miscible in the amorphous state at room temperature. ....	1276
5. Table IV Polymer pairs miscible in the amorphous state at room temperature. Molecular weight dependence investigated. ....	1279
6. Table V Polymer pairs that appear to have high temperature miscibility although immiscible at or below room temperature (UCST behavior). ....	1282
7. Table VI Polymer pairs miscible at room temperature that appear to have a lower critical solution temperature (LCST) above room temperature. ....	1284
8. Table VII Polymer pairs appear to have both a lower critical solution temperature and a upper critical solution temperature. ....	1294
9. Table VIII Polymer pairs that co-crystallize and form mixed crystals. ....	1293
10. References .....	1297
<b>APPENDIX III. Examples of Commercial Blends</b> .....	1323
<i>compiled by L. A. Utracki</i>	
<b>APPENDIX IV. Dictionary of Terms Used in Polymer Science and Technology</b> .....	1333
<i>compiled by L. A. Utracki</i>	
<b>Subject Index</b> .....	1387



2nd ed. â€” Springer New York Heidelberg Dordrecht London, 2014. â€” XXIII, 2378 p. 491 illus., 131 illus. in color. In 3 volumes, not available separately. Explores all aspects of polymer blends science, engineering, technology and application Explains fundamentals and terms used in polymer science and technology Updates researchers on recent developments including nanoparticles containing blends, biodegradable blends and high performance blends. The Polymer Blends Handbook is a fundamental reference work on polymer blends, covering all aspects: science, engineering, technology and application. It will appeal to anyone working in the field of blends, researchers as well as engineers. The Handbook is designed to be the source of information on all aspects of polymer blends. To this end the Editors have put together an international group of highly respected contributors, each an expert in his chosen subjects. About the Author. Start by marking â€œPolymer Blends Handbook, Volume 1 And Volume 2â€ as Want to Read: Want to Read savingâ€; Want to Read.Â Weâ€™d love your help. Let us know whatâ€™s wrong with this preview of Polymer Blends Handbook, Volume 1 And Volume 2 by Leszek A. Utracki. Problem: Itâ€™s the wrong book Itâ€™s the wrong edition Other. The Polymer Blends Handbook is a fundamental reference work on polymer blends, covering all aspects: science, engineering, technology and application. It will appeal to anyone working in the field of blends, researchers as well as engineers. The Handbook is designed to be the source of information on all aspects of polymer blends. To this end the Editors have put together an international group of highly respected contributors, each an expert in his chosen subjects. Show all. @inproceedings{Kulshreshtha2002HandbookOP, title={Handbook of Polymer Blends and Composites}, author={A. Kulshreshtha and C. Vasile}, year={2002} }. A. Kulshreshtha, C. Vasile. Published 2002.